



Technical Data Sheet		SEB™		
		Belt type	SE-H50-SIF	
Applications				
Item		Description		Remarks
Specification	Construction			① White fluoroelastomer (Ground surface) ② Heat resistant fabric (Fabric surface)
	Antistatic	No		
Dimensions	Width	5 to 200 [mm]		
	Length	352 to 1564 [mm]		By molds
	Thickness	0.7 [mm]		
	Joint	Seamless		
Properties	Tensile strength	16.7 [N/mm]		Test speed: 15 %/min.
	Elongation at break	15 [%]		Ambient condition: 23°C,50%R.H.
	Standard elongation	1 to 3 [%]		
	Tension at 2%	2.5 [N/mm]		Ambient condition: 23°C,50%R.H.
	Minimum pulley dia.	15 [mm]		
	Operating temp.	-20 to +200 [°C]		
	Coefficient of friction	0.3 to 0.6(Paper) Fabric surface		Measurement condition: 7kPa,1mm/s
		0.4 to 0.8(Steel) Ground surface		Ambient condition: 23°C,50%R.H.
Mass	1.1 [kg/m ²]			
Features	<ul style="list-style-type: none"> Heat resistance 			