Technical NI Data Sheet		TTA BELT POLY	Ver.2016-02
		XH-1000-6.5	NITTA
Applications			
	Item	Description	Remarks
Specification	Construction	(1) (2) (3) (4) (4)	①Soft NBR (Textured Pattern, Blue) ②PA Fabric ③PA Film ④Soft NBR (Textured Pattern, Blue)
Dimensions	Antistatic	Yes	
	Width	20 to 320 [mm]	
	Length	800 to 52,000 [mm]	
imer	Thickness	6.5 [mm]	
	Joint	Skived joint Adhesive Polybond A and E	
Properties	Tensile strength	300 [N/mm]	Test speed: 50mm/min
	Elongation at break	20 [%]	Ambient condition: 23°C,50%R.H.
	Standard elongation	1 [%]	
	Tension at 1 [%]	7.5 [N/mm]	Ambient condition: 23°C,50%R.H.
	Minimum pulley dia.	100 [mm]	
	Operating temp.	-20 to +80°C	
	Coefficient of	0.8 to 0.9(Paper) / 0.7 to 0.8(Steel) (Both side)	Measurement condition: 7kPa, 1mm/s
	friction		Ambient condition: 23°C,50%R.H.
	Mass	7.2 [kg/m2]	
Features			
			Industrial Products Div.