



Technical Datasheet	PolyBelt™ Belt type	Power Transmission and Conveyor Belt SG-350
		PB-002 Ver.3

Applications

- Sheet-fed printing press
- Rotary printing press
- Light duty conveyor

Construction



<table border="0" style="width: 100%;"> <tr> <td style="padding: 5px;">Top side</td> <td style="padding: 5px;">Bottom side</td> </tr> <tr> <td style="padding: 5px;">Polyamide</td> <td style="padding: 5px;">Polyamide</td> </tr> <tr> <td style="padding: 5px;">-</td> <td style="padding: 5px;">-</td> </tr> <tr> <td style="padding: 5px;">NBR-impreg. fabric</td> <td style="padding: 5px;">NBR-impreg. fabric</td> </tr> <tr> <td style="padding: 5px;">Green</td> <td style="padding: 5px;">Black</td> </tr> </table> <table border="0" style="width: 100%;"> <tr> <td style="padding: 5px;">Tension member</td> <td style="padding: 5px;">Splice</td> </tr> <tr> <td style="padding: 5px;">Polyamide</td> <td style="padding: 5px;">Skiver</td> </tr> <tr> <td style="padding: 5px;">Film</td> <td style="padding: 5px;"></td> </tr> <tr> <td style="padding: 5px;">0.35mm</td> <td style="padding: 5px;"></td> </tr> </table>	Top side	Bottom side	Polyamide	Polyamide	-	-	NBR-impreg. fabric	NBR-impreg. fabric	Green	Black	Tension member	Splice	Polyamide	Skiver	Film		0.35mm		<p>Construction </p>
Top side	Bottom side																		
Polyamide	Polyamide																		
-	-																		
NBR-impreg. fabric	NBR-impreg. fabric																		
Green	Black																		
Tension member	Splice																		
Polyamide	Skiver																		
Film																			
0.35mm																			

<p>Dimensions</p> <table border="0" style="width: 100%;"> <tr><td style="padding: 5px;">Width/Roll (max.)</td><td style="text-align: right; padding: 5px;">325mm</td></tr> <tr><td style="padding: 5px;">Width/Endless (max.)</td><td style="text-align: right; padding: 5px;">300mm</td></tr> <tr><td style="padding: 5px;">Length (max.)</td><td style="text-align: right; padding: 5px;">105m</td></tr> <tr><td style="padding: 5px;">Total thickness</td><td style="text-align: right; padding: 5px;">0.95mm</td></tr> <tr><td style="padding: 5px;">Weight</td><td style="text-align: right; padding: 5px;">0.9 Kg/m²</td></tr> </table> <p style="font-size: small;">Please contact Nitta if you need other dimensions.</p> <p>Regulatory compliance</p> <p>RoHS(2011/65/EC, (EU)2015/863)</p> <p>Features</p> <ul style="list-style-type: none"> Antistatic Moderate C.O.F. Slider bed Roller bed 	Width/Roll (max.)	325mm	Width/Endless (max.)	300mm	Length (max.)	105m	Total thickness	0.95mm	Weight	0.9 Kg/m ²	<p>Properties</p> <p>Minimum pulley diameter</p> <table border="0" style="width: 100%;"> <tr> <td style="padding: 5px;">Power Transmission Application</td> <td style="padding: 5px;">Skiver</td> <td style="text-align: right; padding: 5px;">35mm</td> </tr> <tr> <td style="padding: 5px;">Conveyor Application</td> <td style="padding: 5px;">Skiver</td> <td style="text-align: right; padding: 5px;">30mm</td> </tr> </table> <p>Dynamic properties</p> <table border="0" style="width: 100%;"> <tr> <td style="padding: 5px;">Standard elongation</td> <td style="text-align: right; padding: 5px;">2.0%</td> </tr> <tr> <td style="padding: 5px;">Tension after relaxation at 2.0%</td> <td style="text-align: right; padding: 5px;">5.2N/mm</td> </tr> <tr> <td style="padding: 5px;">Initial tension at 3.0%</td> <td style="text-align: right; padding: 5px;">15.6N/mm</td> </tr> <tr> <td style="padding: 5px;">Tension after relaxation at 3.0%</td> <td style="text-align: right; padding: 5px;">7.8N/mm</td> </tr> <tr> <td style="padding: 5px;">Operating temperature range</td> <td style="text-align: right; padding: 5px;">-20~80°C</td> </tr> <tr> <td style="padding: 5px;">Operating temperature range*</td> <td style="text-align: right; padding: 5px;">-20~80°C</td> </tr> </table> <p style="font-size: x-small; text-align: center;">*When under continuous use</p>	Power Transmission Application	Skiver	35mm	Conveyor Application	Skiver	30mm	Standard elongation	2.0%	Tension after relaxation at 2.0%	5.2N/mm	Initial tension at 3.0%	15.6N/mm	Tension after relaxation at 3.0%	7.8N/mm	Operating temperature range	-20~80°C	Operating temperature range*	-20~80°C	<p>Tensile properties</p> <table border="0" style="width: 100%;"> <tr> <td style="padding: 5px;">Tensile strength</td> <td style="text-align: right; padding: 5px;">105N/mm</td> </tr> <tr> <td style="padding: 5px;">Elongation at break</td> <td style="text-align: right; padding: 5px;">20%</td> </tr> <tr> <td style="padding: 5px;">Maximum allowable tension</td> <td style="text-align: right; padding: 5px;">15.6N/mm</td> </tr> <tr> <td style="padding: 5px;">Maximum allowable elongation</td> <td style="text-align: right; padding: 5px;">3.0%</td> </tr> </table> <p>Coefficient of friction</p> <table border="0" style="width: 100%;"> <tr> <td style="padding: 5px;">Top</td> <td style="padding: 5px;">vs. Steel</td> <td style="text-align: right; padding: 5px;">0.3~0.4</td> </tr> <tr> <td></td> <td style="padding: 5px;">vs. Paper</td> <td style="text-align: right; padding: 5px;">0.4~0.5</td> </tr> <tr> <td style="padding: 5px;">Bottom</td> <td style="padding: 5px;">vs. Steel</td> <td style="text-align: right; padding: 5px;">0.3~0.4</td> </tr> <tr> <td></td> <td style="padding: 5px;">vs. Paper</td> <td style="text-align: right; padding: 5px;">0.4~0.5</td> </tr> <tr> <td></td> <td style="padding: 5px;">vs. Lagged pulley</td> <td style="text-align: right; padding: 5px;">0.5~0.7</td> </tr> <tr> <td></td> <td style="padding: 5px;">vs. POM (resin)</td> <td style="text-align: right; padding: 5px;">0.3~0.5</td> </tr> </table>	Tensile strength	105N/mm	Elongation at break	20%	Maximum allowable tension	15.6N/mm	Maximum allowable elongation	3.0%	Top	vs. Steel	0.3~0.4		vs. Paper	0.4~0.5	Bottom	vs. Steel	0.3~0.4		vs. Paper	0.4~0.5		vs. Lagged pulley	0.5~0.7		vs. POM (resin)	0.3~0.5
Width/Roll (max.)	325mm																																																							
Width/Endless (max.)	300mm																																																							
Length (max.)	105m																																																							
Total thickness	0.95mm																																																							
Weight	0.9 Kg/m ²																																																							
Power Transmission Application	Skiver	35mm																																																						
Conveyor Application	Skiver	30mm																																																						
Standard elongation	2.0%																																																							
Tension after relaxation at 2.0%	5.2N/mm																																																							
Initial tension at 3.0%	15.6N/mm																																																							
Tension after relaxation at 3.0%	7.8N/mm																																																							
Operating temperature range	-20~80°C																																																							
Operating temperature range*	-20~80°C																																																							
Tensile strength	105N/mm																																																							
Elongation at break	20%																																																							
Maximum allowable tension	15.6N/mm																																																							
Maximum allowable elongation	3.0%																																																							
Top	vs. Steel	0.3~0.4																																																						
	vs. Paper	0.4~0.5																																																						
Bottom	vs. Steel	0.3~0.4																																																						
	vs. Paper	0.4~0.5																																																						
	vs. Lagged pulley	0.5~0.7																																																						
	vs. POM (resin)	0.3~0.5																																																						